

**BUSITEMA
UNIVERSITY**
Pursuing Excellence

FACULTY OF ENGINEERING

TEXTILE AND GINNING ENGINEERING DAPARTMENT

**THE SUITABILITY OF UGANDAN MUSA SAPIENTUM
BANANA PLANT SPECIES FOR TEXTILE FIBRE
PRODUCTION**



STUDENT NAME: KASHEMERE DAMARI

REG No: BU/UG/2009/75

kashtdaimal@gmail.com

**A Project Report submitted to the Department of Textile and Ginning Engineering
for the award of a Bachelor of Science Degree in Textile Engineering of Busitema
University**

MAY 2013

DECLARATION

I **Damari Kashemere** do declare to the best of my knowledge that I did this Final Year Project in partial fulfillment of the requirements for the award of a Bachelor of Science in Textile Engineering of Busitema University and that the work here is solely of my own effort, except where reference has been appended. It is in no case a reproduction of any other work.

Damari Kashemere

Signature

28th MAY, 2013

Date



APPROVAL

This report has been submitted for examination with approval from the following supervisors:

MR.: RWAWIIRE SAMSON

Signature.....

Date.....

ENG. WANDERA WAFULA JOHNNIE

Signature.....

Date

ACKNOWLEDGEMENTS

Writing this report at some point seemed like I would never get through. However, with persistence and keen focus, it is finally complete. I want to acknowledge everyone who participated for their help and support, without which this report would not have been finished.

The first is God whose guidance, love, and grace has seen me through writing as well as the publication of this report as a successful venture.

I am also indebted to my supervisors ENG. Rwawire Samson (The Head of department Textile and Ginning Engineering, Busitema University) and ENG. Wandera Wafula Johnnie (The team leader MSI, Busitema University) for their valuable guidance and expert advice. may the Almighty God reward your efforts.

Last but not least, a special cheer for all my fellow students for their enthusiasm, love and encouragement

I wish you success in the struggle to liberate your selves from ignorance, poverty and disease, and may the good Lord richly reward you with success.

DEDICATION

I dedicate this report to my dear Dad and Mum whose sacrifice has seen me into the world of engineering.

LIST OF TABLES

TABLE 1: THE CHEMICAL COMPOSITION OF PSEUDOSTEM FIBERS	12
TABLE 2: TENSILE TEST RESULTS FOR UNTREATED FIBRE	23
TABLE 3: TEST RESULTS FOR FIBRE SCoured AT 2 GPL SOLUTION OF NaOH FOR 30 MINUTES... 24	24
TABLE 4: TEST RESULTS FOR FIBRE SCoured AT 2 GPL SOLUTION OF NaOH FOR 60MINUTES ... 25	25
TABLE 5: TEST RESULTS FOR FIBRE SCoured WITH ASH WATER FOR 30 MINUTES	26
TABLE 6: TEST RESULTS FOR THE FIBRE SCoured WITH ASH WATER FOR 60MINUTES	27
TABLE 7: EFFECT OF THE ALKALI TREATMENT ON THE MECHANICAL FIBRES PROPERTIES	29
TABLE 8: COMPARISON OF UNTREATED FIBRES AND FIBRE TREATED FOR 30MINUTES	30

LIST OF FIGURES

FIGURE 1: ENERGY FOR PRODUCTION OF SOME OF THE NATURAL FIBRES AND CARBON FIBRE	1
FIGURE 2: 2008 GLOBAL FIBRE PRODUCTION: 69MILLION METRIC TONS.....	2
FIGURE 3: A HEAP OF DISPOSED OFF BANANA PSEUDOSTEMS	3
FIGURE 4 : REMOVING THE OUTSIDE PSEUDOSTEM LAYERS, FIG. 5: FRESH STRIPS READY TO BE...	14
FIGURE 6: THE FIBRE EXTRACTION PROCESS FIGURE 7: EXTRACTED BANANA FIBRE	15
FIGURE 8: SCOURED FIBRE.....	16
FIGURE 9: THE BLEACHING PROCESS FIGURE 10: BLEACHED FIBRE WASHING.....	17
FIGURE 11: DRYING OF BLEACHED FIBRE.....	17
FIGURE 12: THE SINGLE END TENSILE TESTER	18
FIGURE 13: SEM MICROGRAPH OF MUSA SAPIENTUM UNTREATED BANANA FIBRE	22
FIGURE 14: STRESS-STRAIN CURVES OF UNTREATED AND TREATED BANANA FIBRE	28

ACRONYMS

Ha	hectare(s)
Kg	kilogram(s)
FAO	Food and Agriculture Organization of the United Nations
ASTM	American Society for Testing and Materials
w/v	weight on volume
w/w	weight on weight
SEM	scanning electron microscopy
GPL	grams per litre
Sd	standard deviation
SE	standard error
C_v	Coefficient of variation
OH	Hydroxyl
COOH	Carboxyl

ABSTRACT

Banana stem has no use after harvesting the fruit; there is a huge generation of waste as a consequence of the plant life-cycle, because pseudostems, hangers and leaves are not economically used. Therefore this study was carried out to analyse the suitability of Ugandan *Musa Sapientum* banana species for the production of textile fibre. The fibre was extracted from the banana pseudostem by hand, morphological characterization of fibres was done, the fibre was scoured using an alkali (NaOH and ash water) and then bleached using hydrogen peroxide. Scouring was done at different NaOH concentrations and ash water at different timings of 30, 60 and 90 minutes respectively. Fibre tensile property testing was done before and after fibre treatment. The fibre morphological properties were analysed before any fibre treatment was done.

Generally *Musa Sapientum* was found to have very robust fibres that could be used in various textile applications as industrial textiles, consumer textiles, furnishing textiles among others.

Musa Sapientum fibre treatment using alkali increases its tensile strength and young's modulus and has got less effect on fibre elongation. Morphological characterisation showed that treated fibres' surface was rougher than that of untreated fibres.

From the results, the optimum scouring conditions for *Musa Sapientum* fibre scouring is using 2g/L of NaOH or ash water of PH.10 for one hour; however ash water treatment gives stronger fibres with higher modulus of elasticity. High figure of young's modulus signifies fibre stiffness.

Key words; *Musa Sapientum* fibre, optimisation, mechanical and physical properties, textile application

2.8.2 <i>The boiling of banana fibres in ash water</i>	13
CHAPTER THREE: METHODS AND MATERIALS	14
3.1 Raw materials.....	14
3.2 Fiber extraction.....	14
3.3 Fibre treatment.....	15
3.3.1 <i>Scouring</i>	15
3.3.2 <i>Bleaching</i>	16
3.4 Determination of fibre properties.....	17
3.4.1 <i>Fibre mechanical properties</i>	18
3.4.2 <i>Fibre morphological property analysis</i>	19
CHAPTER FOUR: RESULTS, ANALYSIS AND DISCUSSIONS	21
4.1 Fibre morphological properties.....	21
4.2 Fibre mechanical properties.....	21
4.2.1 <i>Effect of the alkali treatment on the mechanical fibres properties</i>	28
4.2.2 <i>Comparison of treated fibres with untreated fibres</i>	29
CHAPTER FIVE: CONCLUSIONS AND RECOMMENDATIONS	32
5.1 Conclusions.....	32
5.2 Recommendations.....	32
REFERENCES	34
APPENDICES	a

CHAPTER ONE: INTRODUCTION

1.1 Background

Bananas occupy the largest cultivated area among staple food crops in Uganda and are primarily grown on small subsistence farms (plots of less than 0.5 ha). In general, the Great Lakes region covering parts of Uganda, Rwanda, Burundi, Tanzania, Kenya and DRC is the largest producer and consumer of bananas in Africa (Smale, 2006) where per capita consumption has been estimated at more than 250kg; the highest in the world (FAO, 1985). Specifically, Uganda ranks second after India in the world banana production with an annual output of 9.84 million tones accounting for 11.18% of the world's total production (INIBAP, 1999). The area under banana production is 1.3 million hectares and this constitutes 75% of arable land (NARO, 2000).

In recent years, the search for alternative sources of fibers has been increasing due to the continuous reduction of cotton yields, the main textile fibre in Uganda and other countries. There have been many solutions to this problem; like substitution with the manmade fibres, extraction from other natural fiber producing plants which has tried to overcome the shortage. Synthetic fibres/manmade fibres have proved to take up the biggest percentage in the problem solving (see figure 2), however these fibres are not eco-friendly because of their non-biodegradable nature which has raised much environmental concern. More so these synthetics are not recyclable and their manufacturing process is not an easy venture due to the large quantum of energy needed during their production process (for example; figure 1)




Figure 1: Energy for production of some of the natural fibres and carbon fibre (Sources: SachsenLeinen; Daimler 1999; BAFA;NOVA; AVB; CELC; REO)